

PRODUCT DATA SHEET

Sikafloor® Marine-530

IMO approved self-levelling, 2-component polyurethane decorative resin

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	Sikafloor® Marine-530 (A)	Sikafloor® Marine-530 (B)
Chemical Base	Polyurethane	Isocyanate
Color (CQP001-1)	mixed	Coloured
		Yellowish
		Various colours available (see color design chart)
Density	mixed	1.2 kg/l
		1.2 kg/l
Solid Content		100 %
Mixing Ratio	by weight	79 : 21
Application Temperature	substrate / climate	10 – 30 °C ^{A, B}
Working Time	10 °C	21 minutes
	20 °C	15 minutes
	30 °C	12 minutes
Shore A Hardness (CQP023-1 / ISO 48-4)		83
Tensile Strength (DIN 53504)		8 MPa
Elongation at Break (DIN 53504)		180 %
Shelf Life	9 months ^C	12 months ^C

CQP = Corporate Quality Procedure ^{A)} Substrates must be 3 °C above the dew point

^{B)} max. 80 % r.h.

^{C)} stored in sealed container in up-right position in a dry place between 5 and 30 °C, protected from direct sunlight

DESCRIPTION

Sikafloor® Marine-530 is a 2-component, polyurethane, elastic, low VOC self-smoothing marine flooring resin. It is part of the Sikafloor® Marine decorative resin systems.

Sikafloor® Marine-530 has been tested according to FTP Code system and approved according to the IMO Marine Equipment Directives.

PRODUCT BENEFITS

- Good application characteristics
- Very low VOC emission
- IMO Approved
- Solvent-free
- Longterm elastic
- Good mechanical resistance
- IMO approved, as floor covering up to a max. of 2.6 kg/m²

AREAS OF APPLICATION

Sikafloor® Marine-530 can be used interior as wearing layer levelling compound in ship and boat construction. For interior comfort floor solution and exterior as a black deck caulking in the Sikafloor® Marine Deco Teak solutions.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

CURE MECHANISM

The curing of Sikafloor® Marine-530 takes place by a chemical reaction of the two components.

Higher temperatures speed up and lower temperatures slow down the curing process.

CHEMICAL RESISTANCE

For advice contact the Technical Department of Sika Industry.

METHOD OF APPLICATION

Surface Preparation

In the case of cementitious substrates, it must be ensured that the laitance layer is completely removed. This is usually achieved by grinding. All dust, loose and friable material must be completely removed by vacuum before the next application.

Repairs to the substrate, filling of cracks, holes/voids or surface levelling must be carried out first. Repair areas must be cured before applying primers.

Ensure the substrate moisture content is equal or less than 4 % (Calcium carbide method (CM-method)). Apply Sikafloor®-150/-151 as a primer to obtain a closed pore free surface.

2-C polyurethane substrates need usually to be sanded with 40 – 80 grit sanding paper up to diamond disc. In case the substrate is not clean, it is required to clean it before the sanding process to ensure no debris is sanded into the surface. All dust, loose and friable material must be completely removed from the surface by vacuum cleaning before next application.

For more information and other substrates refer to the Sika Pre-Treatment Chart for Sikafloor® Marine Applications.

The application area must be protected against dirt, sun light, water and draught.

Mixing Process

Prior to mixing all components, stir part A using the electric mixing equipment.

Add part B to part A and mix continuously for 2 minutes until a uniformly mix has been obtained. To ensure thorough mixing pour materials into a clean container and mix again for at least 1 minute to achieve a smooth consistent mix.

Excessive mixing must be avoided to minimize air entrainment.

For areas with cambers or slopes (1 – 3 %) SikaLiquid Thickener or Sika® Extender T may be added to adapt the consistency of the product.

Remark: By adapt the consistency, the de-airing properties may be affected.

Application

Sikafloor® Marine-530 is poured and spread evenly by means of a suitable trowel or pin leveller. A spike roller may be used to improve levelling and de-airing.

For liquid application on cambers and slopes multiple applications steps might be needed.

A seamless finish can be achieved when a "wet" edge is maintained during application.

Curing

Indications regarding curing details see table below.

Temperature	Walk- and overcoatable	Full loading
10 °C	36 hours	7 days
20 °C	24 hours	7 days
30 °C	16 hours	7 days

Removal

Uncured Sikafloor® Marine-530 can be removed from tools and equipment with Sika® Colma Cleaner or another suitable solvent. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

Application Limits

Beware of condensation. The substrate and uncured applied product must be at least 3 °C above dew point to reduce the risk of condensation.

Freshly applied Sikafloor® Marine-530 must be protected from damp, condensation and water for at least 1 day. Uncured material reacts in contact with water (foaming).

For consistent color matching, ensure the product in each area is applied from the same batch numbers.

For air heating use only electric powered warm air blower systems.

If Sikafloor® Marine-530 is used in interior areas and exposed to UV light, the floor must be protected by a pigmented sealer, such as Sikafloor® Marine-505.

STORAGE CONDITIONS

The product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.

After opening of the packaging, the contents need to be protected against moisture.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Sika Pre-Treatment Chart for Sikafloor® Marine Application

PACKAGING INFORMATION

Sikafloor® Marine-530 (A)

Container	15.8 kg
-----------	---------

Sikafloor® Marine-530 (B)

Container	4.2 kg
-----------	--------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

Sikafloor® Marine-530
Version 06.01 (11 - 2024), en_MY
012119015304001000

Sika Kimia Sdn. Bhd.

Lot 689, Nilai Industrial Estate,
71800 Nilai, Negeri Sembilan D.K.
Malaysia
Phone: +606-7991762
e-mail: info@my.sika.com
Website: www.sika.com.my

